

PLEXIGLAS® Optical POQ66

Product Profile:

PLEXIGLAS® Optical POQ66 is an amorphous thermoplastic molding compound based on polymethylmethacrylate (PMMA).

In addition to the familiar properties of PLEXIGLAS® molding compounds, such as

- excellent light transmission and brilliance,
- very good weather resistance,
- high mechanical strength, surface hardness and mar resistance,

PLEXIGLAS® Optical POQ66 is distinguished by its

- guaranteed purity and clarity,
- high luminous efficiency in medium to long light paths,
- absolute colorlessness even in thick layers.

Application:

PLEXIGLAS® Optical POQ66 is suitable for manufacturing extruded sheets to meet stringent optical requirements.

Examples:

Small to medium-sized injection-molded or injection compression-molded lightguide panels for display applications, lightguides.

Processing:

PLEXIGLAS® Optical POQ66 can be processed on extruders with conventional three-section screws for engineering thermoplastics.

For manufacturing extruded lightguide panels, it is advisable to maintain processing temperatures at the lower end of the scale.

Physical Form / Packaging:

PLEXIGLAS® Optical POQ66 is supplied as pellets of uniform size in big-bags; other packaging on request.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Optical POQ66
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3200
Stress @ Break	5 mm/min	MPa	ISO 527	69
Strain @ Break	5 mm/min	%	ISO 527	4
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	104
Glass Transition Temperature		°C	IEC 10006	108
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	8
Fire Rating			DIN 4102	B2
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	2.9
Optical Properties				
Luminous transmittance	d=3 mm			
	D65	%	ISO 13468-2	92
Refractive Index			ISO 489	1.49
Other Properties				
Density		g/cm ³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		max. 94
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Die Temperature (Extrusion)		°C		220 – 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt
Telefon +49 6151 18-4711 Telefax +49 6151 18-3177
www.plexiglas-polymers.com

Ref. No.: MC139-E v0160 Date: 2011-04-04