

PLEXIGLAS® Satinice df20 8N

Product Profile:

PLEXIGLAS® Satinice df20 8N based on PLEXIGLAS® 8N are characterized by diffuse scattering of light.

Besides showing the familiar properties of standard PLEXIGLAS® molding compound, such as

- excellent weatherability,
- high surface hardness and mar resistance,

PLEXIGLAS® Satinice df20 8N is special in that they combine

- good diffusing power with excellent light transmission.

Application:

Used for injection molding items for lighting engineering applications

Examples:

displays, fiber optics, projection screens, lighting fixtures and similar applications in lighting engineering.

Processing:

PLEXIGLAS® Satinice df20 8N can be processed on injection molding machines with 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Satinice df20 8N is supplied as pellets of uniform size, packaged in two-ply, 25kg polyethylene bags; other packaging on request.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Satinice df20 8N
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3300
Stress @ Break	5 mm/min	MPa	ISO 527	74
Strain @ Break	5 mm/min	%	ISO 527	5
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	19
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	108
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	103
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	98
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	6.3
Fire Rating			DIN 4102	B2
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	2.5
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	88
Half-Value Angle		°	DIN 5036	1.6
Other Properties				
Density		g/cm ³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		max. 95
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Mold Temperature (Injection Molding)		°C		60 – 90

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt
 Telefon +49 6151 18-4711 Telefax +49 6151 18-3177
 www.plexiglas-polymers.com

Ref. No.: MC10-E v0160 Date: 2011-04-04