

## PLEXIGLAS® Satinice df23 zk6BR

---

### Product Profile:

PLEXIGLAS® Satinice df23 zk6BR, based on PLEXIGLAS® Resist zk6BR, is an impact modified molding compound characterized by diffuse scattering of light.

Typical properties of impact modified PLEXIGLAS® molding compound are

- high break resistance and impact strength
- improved resistance to stress cracking
- good weather resistance
- high surface hardness and mar resistance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® df23 zk6BR is characterized by the following special properties:

- excellent lightdiffusion combined with excellent light transmission
- matte surfaces can be obtained by varying the extrusion parameters.

### Application:

Used for extruding profiles and sheets, but also for injection molding items for lighting engineering applications

### Examples:

applications that call for light diffusion combined with optimum transmission

### Processing:

PLEXIGLAS® Satinice df23 zk6BR can be processed on extruders with 3–zone general purpose screws for engineering thermoplastics.

The matte finish of profile surfaces depends very much on machine design (calibrating unit, polishing rolls) and cooling conditions. It can be enhanced by controlled temperature reduction.

### Physical Form / Packaging:

PLEXIGLAS® Satinice df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

## Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Satinice df23 zk6BR
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	1900
Yield Stress	50 mm/min	MPa	ISO 527	46
Yield Strain	50 mm/min	%	ISO 527	5
Nominal Strain @ Break		%	ISO 527	36
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	50
Charpy Notched Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1	6
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	91
Glass Transition Temperature		°C	IEC 10006	107
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	99
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	93
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	9
Fire Rating			DIN 4102	B2
Glow Wire Ignition Temperature		°C	IEC 60695-2	700
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3.8kg	cm <sup>3</sup> /10min	ISO 1133	1.3
<b>Optical Properties</b>				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	81
Half-Value Angle		°	DIN 5036	21
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.15
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 80
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		230 – 260
Die Temperature (Extrusion)		°C		ca. 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

---

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt  
Telefon +49 6151 18-4711 Telefax +49 6151 18-3177  
[www.plexiglas-polymers.com](http://www.plexiglas-polymers.com)

Ref. No.: MC128-E3 v0160 Date: 2011-04-04

---