

## PLEXIGLAS® Resist zk4HC

---

### Product Profile:

PLEXIGLAS® Resist zk4HC is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk4HC is characterized by the following special properties:

- improved break resistance and impact strength
- best resistance to stress cracking of all impact-modified PLEXIGLAS molding compounds
- AMECA listing.

### Application:

Used for extruding and coextruding sheets and profiles.

### Examples:

extruded/coextruded sheets and profiles for automotive bodies and the sanitaryware sector (bathtubs and shower trays) or crystal-clear luminare covers for industrial plants that come into contact with aggressive media.

### Processing:

PLEXIGLAS® Resist zk4HC can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

### Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

## Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Resist zk4HC
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	2900
Yield Stress	50 mm/min	MPa	ISO 527	68
Yield Strain	50 mm/min	%	ISO 527	4.5
Nominal Strain @ Break		%	ISO 527	17
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	25
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	102
Glass Transition Temperature		°C	IEC 10006	108
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	*
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	*
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	8
Fire Rating			DIN 4102	B2
Flammability UL 94	1.6 mm	Class	IEC 707	HB
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3.8kg	cm <sup>3</sup> /10min	ISO 1133	1.1
<b>Optical Properties</b>				
	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	92
Refractive Index			ISO 489	1.49
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.18
Water Absorption in Water		%	ISO 62	2
Humidity Absorption	23°C / 50%	%	ISO 62	0.6
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 90
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Die Temperature (Extrusion)		°C		220 – 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

---

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt  
Telefon +49 6151 18-4711 Telefax +49 6151 18-3177  
[www.plexiglas-polymers.com](http://www.plexiglas-polymers.com)

Ref. No.: MC129-E3 v0160 Date: 2011-04-04

---