

## PLEXIGLAS® Resist zk4HC

### Product Profile:

PLEXIGLAS® Resist zk4HC is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk4HC is characterized by the following special properties:

- improved break resistance and impact strength
- best resistance to stress cracking of all impact-modified PLEXIGLAS molding compounds
- AMECA listing.

### Application:

Used for extruding and coextruding sheets and profiles.

### Examples:

extruded/coextruded sheets and profiles for automotive bodies and the sanitaryware sector (bathtubs and shower trays) or crystal-clear luminare covers for industrial plants that come into contact with aggressive media.

### Processing:

PLEXIGLAS® Resist zk4HC can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

### Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

### For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS® (<http://www.campusplastics.com>) free of charge.

## Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Resist zk4HC
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	2900
Yield Stress	50 mm/min	MPa	ISO 527	68
Yield Strain	50 mm/min	%	ISO 527	4.5
Nominal Strain @ Break		%	ISO 527	17
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	25
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	102
Glass Transition Temperature		°C	ISO 11357	108
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	*
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	*
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	8
Classes of construction product			DIN EN 13501-1	E
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3.8kg	cm <sup>3</sup> /10min	ISO 1133	1.1
<b>Optical Properties</b>				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	92
Refractive Index	589nm/23°C		ISO 489	1.49
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.18
Water Absorption in Water	saturation, 23°C	%	ISO 62	2
Humidity Absorption	23°C / 50%	%	ISO 62	0.6
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 90
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 260
Die Temperature (Extrusion)		°C		220 - 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

CAMPUS is a registered trademark of Chemie Wirtschaftsförderungs-GmbH, Frankfurt / M.

Röhm GmbH • Dolivostraße 17 • 64293 Darmstadt  
plexiglas.polymers@roehm.com  
www.plexiglas-polymers.de  
www.roehm.com

Ref. No.: MC129-E3 A1142 Date: 2019-08-27