

## PLEXIGLAS® Resist zk6BR

---

### Product Profile:

PLEXIGLAS® Resist zk6BR is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are:

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk6BR is characterized by the following special properties:

- maximum break resistance and impact strength,
- improved resistance to stress cracking
- balanced property profile
- AMECA listing.

### Application:

Used for extruding and coextruding sheets and profiles as well as for injection molding

### Examples:

extruded and injection-molded luminaire covers, extruded hollow profiles, writing utensils such as stencils and fountain pens, appliance housings, coextruded profiles for window frames, gutters, downspouts, and housewares such as cutlery handles, bowls, cookie jars.

### Processing:

PLEXIGLAS® Resist zk6BR can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

### Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

### For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS® (<http://www.campusplastics.com>) free of charge.

## Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Resist zk6BR
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	1800
Yield Stress	50 mm/min	MPa	ISO 527	45
Yield Strain	50 mm/min	%	ISO 527	5
Nominal Strain @ Break		%	ISO 527	54
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	80
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	95
Glass Transition Temperature		°C	ISO 11357	109
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	93
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	88
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	11
Classes of construction product			DIN EN 13501-1	E
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3.8kg	cm <sup>3</sup> /10min	ISO 1133	1.6
<b>Optical Properties</b>				
Luminous transmittance	d=3 mm	%	ISO 13468-2	91
Haze			ASTM D1003	< 2
Refractive Index	589nm/23°C		ISO 489	1.49
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.16
Water Absorption in Water	saturation, 23°C	%	ISO 62	1.8
Humidity Absorption	23°C / 50%	%	ISO 62	0.5
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 85
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Mold Temperature (Injection Molding)		°C		50 – 70

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

---

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH.

CAMPUS is a registered trademark of Chemie Wirtschaftsförderungs-GmbH, Frankfurt / M.

Evonik Performance Materials GmbH Kirschenallee 64293 Darmstadt  
plexiglas.polymers@evonik.com  
www.plexiglas-polymers.com

Ref. No.: MC115-E3 a1142 Date: 2018-03-28

---