

## PLEXIGLAS® Resist zk6HC

---

### 产品概述:

宝克力® 抗冲击 zk6HC 是一种无定形热塑性模塑料 (PMMA).

PLEXIGLAS® 抗冲改性模塑料常见的性能如下:

- 高耐候性
- 高透光性和纯净度
- 高光泽度
- 良好的注塑体验以及注塑时较为安静

宝克力® 抗冲击 zk6HC 特殊性能如下:

- 优异的耐断裂性和抗冲强度
- 最好的耐应力性能相比其他改性宝克力模塑料

### 应用:

挤出以及共挤的制件, 板材, 型材等

### 应用实例:

挤出共挤的板材和型材, 用于汽车车体或者洁具用品 (浴缸或者淋浴房底座) 或者经常接触较强环境的水晶效果的发光面罩等。

### 加工方法:

宝克力® 抗冲击 zk6HC 可用常见的三段式注塑机注塑成型为工程用的热塑性塑料

### 模塑料物理形态/包装:

宝克力® 抗冲击 zk6HC 模塑料成品是粒径均匀的粒料, 以聚乙烯袋每25公斤包装或以配有聚乙烯内衬的箱子每500公斤包装; 也可应顾客要求包装。

产品性能参数:

	测试参数	单位	测试标准	zk6HC
<b>力学性能</b>				
拉伸模量	1 mm/min	MPa	ISO 527	1700
屈服应力	50 mm/min	MPa	ISO 527	47
屈服应变	50 mm/min	%	ISO 527	5.5
断裂伸长率		%	ISO 527	48
卡毕冲击强度	23 °C	kJ/m <sup>2</sup>	ISO 179/1eU	80
<b>热性能</b>				
维卡软化温度	B / 50	°C	ISO 306	97
线性热膨胀系数	0 - 50 °C	E-5 /°K	ISO 11359	11
建筑产品耐火等级			DIN EN 13501-1	E
耐火等级	1.6 mm	Class	IEC 60695-11-10	HB
<b>流变性能</b>				
熔体流动速率, MVR	230°C /3.8 kg	cm <sup>3</sup> /10 min	ISO1133	0.4
<b>光学性能</b>				
透光率	D65, 3 mm	%	ISO 13468-2	91
折射率			ISO 489	1.49
<b>其他性能</b>				
密度		g/cm <sup>3</sup>	ISO 1183	1.16
水中吸水率		%	ISO 62	1.8
吸水率	23°C /50 %	%	ISO 62	0.5
<b>推荐加工条件</b>				
预干燥温度		°C		最高 85
干燥时间		h		2-3
熔化温度		°C		220-260
模头温度 (挤出温度)		°C		220-260

本页所有数据是材料代表性数据, 仅供参考。本公司无义务提供本页数据, 所示内容也不代表本公司产品规格。

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Ref. No.:MC117-E3 V0160 Date: 2011-04-04

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt

Telefon +49 6151 18-4711 Telefax +49 6151 18-3177