

PLEXIGLAS® Hi-Gloss FT15 black 9V022

Product Profile:

PLEXIGLAS® Hi-Gloss FT15 black 9V022 is a special acrylic-based polymer.

With regard to its

- high mar resistance
- good weather resistance
- good polishability,

PLEXIGLAS® Hi-Gloss FT15 9V022 shows comparable properties to those of PLEXIGLAS® standard molding compounds. In addition, PLEXIGLAS® Hi-Gloss FT15 9V022 offers the special benefit of a

- high heat deflection temperature combined with good flow.

Application:

PLEXIGLAS® Hi-Gloss FT15 9V022 is particularly suitable for injection molding technical components. Owing to its superior brilliance, high-gloss (Class A) black surfaces can be obtained in.

Examples:

add-on automotive body parts

Processing:

PLEXIGLAS® Hi-Gloss FT15 black 9V022 can be processed on injection-molding machines with for PMMA suitable 3-zone-screw. Good pre-desiccation must be pointed out.

Physical Form / Packaging:

PLEXIGLAS® Hi-Gloss FT15 black 9V022 is supplied as pellets of uniform size, packaged in 25kg, two-ply polyethylene bags; other packaging on request.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Hi-Gloss FT15 black 9V022
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3500
Stress @ Break	5 mm/min	MPa	ISO 527	50
Strain @ Break	5 mm/min	%	ISO 527	3.1
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	18
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	115
Glass Transition Temperature		°C	ISO 11357	121
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	107
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	105
Classes of construction product			DIN EN 13501-1	E
Glow Wire Ignition Temperature		°C	IEC 60695-2	675
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	4.5
Other Properties				
Density		g/cm ³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		100
Predrying Time in Desiccant-Type Drier		h		4 - 6
Melt Temperature		°C		220 - 250
Mold Temperature (Injection Molding)		°C		70 - 95

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

Röhm GmbH • Dolivostraße 17 • 64293 Darmstadt
 plexiglas.polymers@roehm.com
 www.plexiglas-polymers.com
 www.roehm.com

Ref. No.: MC135-E A1142 Date: 2019-08-27