

PLEXIGLAS® Hi-Gloss NTA-3

产品概述:

宝克力® 高光泽NTA-3是一种具有高热变形温度基于PMMA的模塑料。

除了具有PLEXIGLAS® 模塑料常见的性能:

- 良好的流动性
- 高耐刮擦性
- 强耐候性
- 高光泽度

PLEXIGLAS® Hi-Gloss NTA-3特殊性能如下:

- 较高的负载下热变形温度

应用:

PLEXIGLAS® Hi-Gloss NTA-3尤其适合于注塑件。

由于材料的超高亮度, 所得的非透明注塑件, 能获得高光泽度 (A等级) 的表面

应用实例:

汽车车身饰件: 车窗导轨, 立柱板

加工方法:

PLEXIGLAS® 高光泽NTA-3 可用常见的三段式注塑机注塑成型为工程用的热塑性塑料

模塑料物理形态/包装:

PLEXIGLAS® 高光泽NTA-3 模塑料成品是粒径均匀的粒料, 以聚乙烯袋每25公斤包装或以配有聚乙烯内衬的箱子每500公斤包装; 也可应顾客要求包装。

产品性能参数:

	测试参数	单位	测试标准	NTA-3
力学性能				
拉伸模量	1 mm/min	MPa	ISO 527	2900
断裂应力	5 mm/min	MPa	ISO 527	60
断裂伸长率	5 mm/min	%	ISO 527	2.6
卡毕冲击强度	23 °C	kJ/m ²	ISO 179/1eU	16
热性能				
维卡软化温度	B / 50	°C	ISO 306	116
玻璃化转变温度		°C	ISO11357	126
负载下的热变形温度	0.45 MPa	°C	ISO 75	106
负载下的热变形温度	1.8 MPa	°C	ISO 75	106
耐火等级			DIN 4102	B2
灼热丝起燃性温度		°C	IEC 60695-2	675
流变性能				
熔体流动速率, MVR	230 °C / 3.8 kg	cm ³ /10 min	ISO1133	2
其他性能				
密度		g/cm ³	ISO 1183	1.18
吸水率		%	ISO 62	>3
推荐加工条件				
预干燥温度		°C		最高 100
干燥时间		h		2-3
熔化温度		°C		220-250
模温 (注塑温度)		°C		50-85

本页所有数据是材料代表性数据, 仅供参考。本公司无义务提供本页数据, 所示内容也不代表本公司产品规格。

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Ref. No.:PP-AP-SHTC01 Date: 2011-08-03

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt

Telefon +49 6151 18-4711 Telefax +49 6151 18-3177

赢创.创新原动力

