

PLEXIGLAS® Satinice df22 zk30

Product Profile:

PLEXIGLAS® Satinice df22 zk 30 is an amorphous, impact-modified thermoplastic molding compound.

Typical properties of impact modified PLEXIGLAS® molding compounds are:

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Satinice df22 zk30 is characterized by the following special properties:

- good light diffusion combined with excellent light transmission
- matte surfaces can be obtained by varying the extrusion parameters
- good break resistance and impact strength
- improved resistance to stress cracking
- balanced property profile

Application:

PLEXIGLAS® Satinice df22 zk 30 is used for injection molding as well as for extruding and coextruding panels and profiles.

Examples:

Displays, extruded and injection molded luminaire covers, extruded hollow profiles, writing utensils, housings, coextruded profiles for window frames, gutters, downspouts, and houseware such as cutlery handles, bowls, cookie jars, etc.

Processing:

PLEXIGLAS® Satinice df22 zk30 molding compound can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Satinice df22 zk30 molding compound is supplied as pellets of uniform size in 25kg PE-bags or 500kg octabins.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Satinice df22 zk30
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	2200
Yield Stress	50 mm/min	MPa	ISO 527	54
Yield Strain	50 mm/min	%	ISO 527	4.3
Nominal Strain @ Break		%	ISO 527	23
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	33
Charpy Notched Impact Strength	23°C	kJ/m ²	ISO 179/1eA	3.1
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	102
Glass Transition Temperature		°C	ISO 11357	112
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	103
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	101
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	9.6
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB**
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	1.1
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	86
Half-Value Angle		°	DIN 5036	11
Other Properties				
Density		g/cm ³	ISO 1183	1.16
Recommended Processing Conditions				
Predrying Temperature		°C		< 85
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 250
Mold Temperature (Injection Molding)		°C		50 - 70

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

Röhm GmbH • Dolivostraße 17 • 64293 Darmstadt
plexiglas.polymers@roehm.com
www.plexiglas-polymers.de
www.roehm.com

Ref. No.: MC284-E3 A1142 Date: 2019-08-27