

## PRODUCT INFORMATION

# PLEXIGLAS® Softlight 7H df22

### Product Profile:

PLEXIGLAS® Softlight 7H df22, based on PLEXIGLAS® 7H, is characterized by diffuse scattering of light.

Typical properties of PLEXIGLAS® molding compound are

- good flow
- high mechanical strength, surface hardness and mar resistance
- very good weather resistance.

Special properties of PLEXIGLAS® Softlight 7H df22 are

- very good lightdiffusion combined with excellent light transmittance
- matte surfaces can be obtained by varying the extrusion parameters.

### Application:

Used for extruding profiles and sheets for lighting engineering applications

### Examples:

Luminaire covers, displays, projection screens and similar lighting applications

### Processing:

PLEXIGLAS® Softlight 7H df22 can be processed on extruders with 3-zone general purpose screws for engineering thermoplastics.

The matte finish of profile surfaces depends very much on machine design (calibrating unit, polishing rolls) and cooling conditions. It can be enhanced by controlled temperature reduction.

### Physical Form / Packaging:

PLEXIGLAS® Softlight df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

### For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS® (<http://www.campusplastics.com>) free of charge.

**Properties:**

	Parameter	Unit	Standard	PLEXIGLAS® Softlight 7H df22
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	3400
Stress @ Break	5 mm/min	MPa	ISO 527	70
Strain @ Break	5 mm/min	%	ISO 527	6
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	20
Charpy Notched Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1	1,8
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	105
Glass Transition Temperature		°C	ISO 11357	108
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	101
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	97
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	6.3
Classes of construction product			DIN EN 13501-1	E
Glow Wire Ignition Temperature		°C	IEC 60695-2	700
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3,8kg	cm <sup>3</sup> /10min	ISO 1133	1,1
<b>Optical Properties</b>				
	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	86
Half-Value Angle		°	DIN 5036	12,5
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.19
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 95
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 260
Die Temperature (Extrusion)		°C		220 - 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer.

Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

Röhm GmbH • Darmstadt • Germany  
plexiglas.polymers@roehm.com  
www.plexiglas-polymers.com

Ref. No.: MC506 A1142

The logo for Röhm, featuring the word "RÖHM" in a bold, black, sans-serif font. The letter "R" is significantly larger than the other letters, and the "O" has a small circle above it, resembling a registered trademark symbol.