

## PRODUCT INFORMATION

# PLEXIMID® TT50

### Product Profile:

PLEXIMID® TT50 is a highly heat distortion-resistant poly(n-methyl methacrylimide) (PMMI).

Besides showing the properties common to all PLEXIMID® molding compounds, such as

- high heat deflection temperature under load,
- excellent transmission and clarity,
- very high strength and rigidity, as well as
- good weather resistance.

PLEXIMID® TT50 is special in that it is

- listed by AMECA.

### Application:

PLEXIMID® molding compound is particularly suitable for injection molding of items meant for applications that involve high heat loads.

### Examples:

automotive lighting, light guides, lenses, fiber optics, luminaire covers, sight glasses, cover lenses.

### Processing:

PLEXIMID® molding compound can be processed on injection molding machines and extruders with PMMA suited 3-zone general purpose screws for thermoplastics.

Note: After a partial removal, we strongly recommend resealing the container in order to prevent permeation of moisture.

### Physical Form / Packaging:

PLEXIMID® is supplied as pellets of uniform size in aluminum-laminated, 25kg polyethylene bags; other packaging on request.

### For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS®

(<http://www.campusplastics.com>) free of charge.

**Properties:**

	Parameter	Unit	Standard	PLEXIMID® TT50
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	4000
Stress @ Break	5 mm/min	MPa	ISO 527	80
Strain @ Break	5 mm/min	%	ISO 527	3
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	20
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	150
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	146
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	142
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	5.3
Classes of construction product			DIN EN 13501-1	E
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	260°C / 10kg	cm <sup>3</sup> /10min	ISO 1133	5
<b>Optical Properties</b>				
	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	91
Refractive Index	589nm/23°C		ISO 489	1,53
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.21
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 100
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		250 - 280
Mold Temperature (Injection Molding)		°C		ca. 110

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

Röhm GmbH • Darmstadt • Germany  
plexiglas.polymers@roehm.com  
www.plexiglas-polymers.com

Ref. No.: MC226 A1142

